



# NATIONAL TESTING LABORATORY PVT. LTD.

F.No. FO1 (5.10)

B-265, Mangolpuri Industrial Area, Phase-I, Delhi-110083  
Ph. : 011-32469295, 27912990-93 (4 Lines), Tel/fax : 011-27912993  
Email: ntdelhi@yahoo.co.in, Visit us: www.nationaltestinglaboratory.net

## TEST-REPORT

Issued to:

J.K.D Plastic  
Industrial Area,  
Panipat-132103 (HR)

Report No.:- 150415GEN167252


Date of Report:- 25/04/2015

Your Ref. No.:- Nil

Date of Receipt: 15/04/2015

Sample Description :- PVC Celuka Board

S.No. Test	Test Method	Test Result
1. Density, kg/m <sup>3</sup>	IS 2380(Pt-III):1977	553
2. Hardness, Shore D	IS 13360(Pt-5/Sec-11) : 1992	56
3. Water Absorption, %	IS 2380(Pt-XVI):1977	0.4
4. Tensile Strength, N/mm <sup>2</sup>	IS 2380(Pt-VI):1977	6.0
5. Elongation at Break, %	IS 2380(Pt-VI):1977	4
6. Vicat Softening Temp. °C	IS 12235(Pt-2):2004	78
7. Coefficient of liner Expansion, mm/mm/°C	ISO 11359	1.5x10 <sup>-5</sup>



\*\*\*\*\*

Lab Incharge

Authorised Signatory

- (1) The results listed refer only to tested samples and applicable parameters. Endorsement of product is neither inferred nor implied.
- (2) Total liability of our Lab is limited to the invoiced amount.
- (3) Samples will be destroyed after 90 days from the date of test report unless otherwise specified.
- (4) This report is not to be reproduced wholly or in part and cannot be used as an evidence in the court of Law and should not be used in any advertising media without our special permission in writing
- (5) Report refer to the sample submitted to us and not drawn by us unless mentioned otherwise.